

Auxiliaries

IC – 212 2K Soft Putty (BPO)

Product Description






Very fine particles, good filling power, fast drying, excellent adhesion power, easy to apply and to sand. Suitable for bare metal, primers and existing finishes.

Technical Characteristics

Color: Yellow Shelf life: 12 months at 25°C

Pre-treatment

Clean surface with water and soap. Rinse and dry.
Degrease with IC – 800
Mechanical sanding with P80. Sand with P150 or P180 to featheredge.
Re-clean with IC – 800

	Mixing Ratio	IC – 212 Soft Putty Hardener (tube) (5 – 15°C (15 – 25°C) (25 – 35°C)	– (vol) 100 g – (vol) 3 g 2 g 1.5 g
Mix well before application.			
	Potlife	7 – 8 mins at 25°C	
	Application	Apply with plastic/steel blade.	
	Drying	Drying at 25°C: 15 – 20 mins	
	Sanding	Wet flat with P180 – 240 grade paper or dry flat with P80-120 grade paper, then with P240 – P320 grade paper to feather edge.	

The products are suitable for professional use only. The data contained in this publication are based on our current knowledge and experience. You can obtain the latest version of technical data sheet from our website at www.wonder-global.com or directly from your supplier.