

Primers

IC – 981 2K Primer Surfacer(Grey)

Product Description






Multi-purpose primer surfacer for covering putty/existing finishes,easy sanding,high efficiency with strong filling power and adhesion. Fine hardness is featured.

Technical Characteristics

Color: Grey Shelf life:24 months at 25°C Theoretical spreading rate: 250-300 m2/l (avg) at 1 µm

Pre-treatment

Degrease with IC-800.
Wash off residues and dry thoroughly.
Re-clean with IC-800. The use of a tack rag is recommended.
Wet flat with P600-800 grade paper or dry flat with P240-360 grade paper.

	Mixing Ratio	IC-981	Primer	100 (vol)	100 g
		IC-961	Hardener	25 (vol)	20 g
		IC-950	Thinner	50-60(vol)	30-35 g
		Mix well and strain before application.			
		Note:			
		IC-940 is for temperatures between 5°C – 15°C			
		IC-950 is for temperatures between 15°C – 25°C			
		IC-960 is for temperatures between 25°C – 35°C			
		IC-970 is for temperatures above 35°C.			
	Spray Viscosity Potlife	16 to 20 seconds DIN 4 cup 25°C			
		1.5-2 hours at 25°C			
	Sprayguns	HVLP gravity-feed spraygun	1.5 – 1.7 mm	1.8 – 2.0 bar	15 – 20 cm
		Compliant gravity-feed spraygun	1.6 – 1.8 mm	3.0 – 4.0 bar	20 – 25 cm
	Application	Number of spraycoats: 1 thin + 1 wet coat			
		Flash-off: 5 – 8 mins			
		Film thickness: 80 – 120 µm			
	Drying	Drying	25°C	60°C	
		Dust free after	10 – 15 mins	–	
		Fully cured after	1.5 – 2 hours	30 mins	
Further Treatment		After the dust-free, apply InnoColor basecoat or topcoat.			

The products are suitable for professional use only. The data contained in this publication are based on our current knowledge and experience. You can obtain the latest version of technical data sheet from our website at www.wonder-global.com or directly from your supplier.