



Binders IC-1K160 Balance Binder for Basecoat Color Preparation

Product Description

Binder for InnoColor basecoats. Improves leveling and enhances orientation of aluminum and pearl particles. When 1K160 used in grey metallic colors, it can enhance the sprayed effect.

Technical Characteristics

Color: Milky Shelf life: 24 months at 20°C

Pre-treatment

See process described in TDS of InnoColor Basecoat – Solid Basecoat 2c, Metallic Colors 2c, Red Pearl 2c, Xirallic / Pearlescent Basecoat 3c.

	Stir well before use.		IC-1K160	
Mixing Ratio	IC-1K Solid Basecoat IC-1KS Coarse Alu. Fine Alu. IC-1KX/1KP Pearl	100g: 100g: 100g: 100g:	5-8g 5-8g 5-8g 5-8g 5-8g	
	Note: IC-1K160 can prevent the metallic color with cloudy phenomenon and get a perfect flake control in metallics.			
Spray Viscosity	14 to 19 seconds DIN 4 cup			: :
Application	See process described in TDS	of InnoColor Bas	secoat	
Drying	See process described in TDS c	of InnoColor Bas	ecoat	

The products are suitable for professional use only. The data contained in this publication are based on our current knowledge and experience. Youcan obtain the latest version of technical date sheet from our website at www.wonder-global.com or directly from your supplier.

Guangzhou Wonder Coating Technology Co.,Ltd. China, Tel. (86) 20 3677 4826, www.wonder-global.com, Issue 15 Apr 2019